

**REBAR BILLET CHEMICAL COMPOSITION**

Qualities	Standards	CHEMICAL COMPOSITION (%)										
			%C	%Mn	%Si	%P	%S	%Cu	%V	%N	%B	%Ceq
RB500W	NA ISO 6935-2 NA 8634	min.	-	-	-	-	-	-	-	-	-	-
		max.	0.22	1.60	0.60	0.050	0.050	0.50	-	0.012	-	0.50
B500B	BS 4449:2005	min.	-	-	-	-	-	-	-	-	-	-
		max.	0.22	-	-	0.050	0.050	0.80	-	0.012	0.0008	0.50
B500B	DIN 488:2009	min.	-	-	-	-	-	-	-	-	-	-
		max.	0.22	-	-	0.050	0.050	0.60	-	0.012	0.0008	0.50
GR 40	ASTM A615	min.	-	-	-	-	-	-	-	-	-	-
		max.	-	-	-	0.060	-	-	-	-	-	-
GR 60	ASTM A615	min.	-	-	-	-	-	-	-	-	-	-
		max.	-	-	-	0.060	-	-	-	-	-	-